

1828 - Matte Setting Powder

Weight: 50.00g

Ingredient	INCI	Function	Percent	Wgt (g)	Wgt (oz)
Phase A					
Calcium Carbonate	Calcium carbonate	Texturizer	55.50	27.75	0.98
Kaolin USP	Kaolin	Texturizer	5.00	2.50	0.09
Pigment Blend Bare Neutral	Titanium dioxide, iron oxides	Pigment	1.50	0.75	0.03
Magnesium Stearate	Magnesium stearate	Texturizer	5.00	2.50	0.09
Phase B					
Silica	Silica	Texturizer	10.00	5.00	0.18
Boron Nitride & Serecite	Mica, Boron Nitride	Texturizer	10.00	5.00	0.18
Phase C					
Squalane Light	C13-15 alkane	Emollient	7.00	3.50	0.12
Polymethylsilsequioxane	Polymethylsilsequioxane	Texturizer	3.00	1.50	0.05
Phase D					
Mica Walnut	Mica	Pigment	3.00	1.50	0.05

Procedure

Phase A: Add ingredients to a mortar and blend well with the pestle until color looks uniform.

Phase B: Add to phase A and blend well.

Phase C: pre-mix in separate vessel until well blended. Add to phase A/B slowly and under good stirring.

Phase D: Add with low sheer until color is uniform. Appearance is a free flowing powder.

Properties

Soft-touch, lightly colored matte setting powder with wrinkle blurring. Customize with your preferred pigment blend and intensity.